

Novel Josephson Effect in Triplet Superconductor - Ferromagnet - Triplet Superconductor Junctions

Boris Kastening¹, Dirk K. Morr^{1,2}, Dirk Manske³ and Karl Bennemann¹

¹ *Institut für Theoretische Physik, Freie Universität Berlin, 14195 Berlin, Germany*

² *Department of Physics, University of Illinois at Chicago, Chicago, IL*

³ *Max-Planck-Institut für Festkörperforschung, Heisenbergstrasse 1, 70569 Stuttgart, Germany*

(Dated: February 2, 2008)

We predict a novel type of Josephson effect to occur in triplet superconductor - ferromagnet - triplet superconductor Josephson junctions. We show that the Josephson current, I_J , exhibits a rich dependence on the relative orientation between the ferromagnetic moment and the $\mathbf{d}$ -vectors of the superconductors. This dependence can be used to build several types of *Josephson current switches*. Moreover, we predict an unconventional temperature dependence of I_J in which I_J changes sign with increasing temperature.

PACS numbers: 74.50.+r, 74.45.+c, 74.78.-w

Josephson junctions made of unconventional superconductors have attracted significant interest over the last few years due to their unconventional quantum transport properties [1, 2, 3, 4, 5, 6]. The latter are determined by the formation of low-energy Andreev bound states [7], which, for example, lead to a low-temperature anomaly in the Josephson current [2, 3]. Josephson junctions consisting of triplet superconductors are of particular interest since the superconductors' odd spatial symmetry guarantees the formation of low-energy Andreev states for any orientation of the superconductors in the junction [4, 5, 6].




FIG. 1: Schematic picture of a 1D Triplet Superconductor - Ferromagnet - Triplet Superconductor (TSFTS) Josephson Junction.

In this Letter, we predict a novel type of Josephson effect in one-dimensional (1D) triplet superconductor - ferromagnet - triplet superconductor (TSFTS) junctions (a schematic picture of such a junction is shown in Fig. 1). In particular, we demonstrate a rich dependence of the Josephson current, I_J , on the relative orientation between the ferromagnetic moment, $\mathbf{M}$, in the barrier and the $\mathbf{d}_{L,R}$ -vectors of the left and right triplet superconductor [8], as described by the angles α and θ (see Fig. 1). This dependence can be used to create *Josephson current switches* in which small changes of α or θ can tune the junction between two “current states”, in which I_J

is either “on” ($I_J \neq 0$) or “off” ($I_J \approx 0$), or differs in its direction. These types of two-level systems are of great current interest in the field of quantum information technology [10]. Moreover, we predict that a TSFTS junction leads to a *qualitatively* new temperature dependence of I_J such that in certain cases, I_J changes sign (i.e., its direction) with increasing temperature. Finally, we show that adiabatic changes in the orientation of $\mathbf{d}_{L,R}$ yield a behavior of I_J which is significantly altered from its equilibrium form.

We take the 1D TSFTS junction to be aligned along the z -axis and be described by the Hamiltonian $H = \int dz dz' H(z, z')$, where ($\hbar = 1$)

$$H(z, z') = \sum_{\sigma} \psi_{\sigma}^{\dagger}(z') \delta(z - z') \left[-\frac{\partial_z^2}{2m} - \mu \right] \psi_{\sigma}(z) + \left\{ \frac{\Delta(z, z')}{2} \left[e^{-i\theta_j} \psi_{\uparrow}^{\dagger}(z') \psi_{\uparrow}^{\dagger}(z) - e^{i\theta_j} \psi_{\downarrow}^{\dagger}(z') \psi_{\downarrow}^{\dagger}(z) \right] + \text{h.c.} \right\} - \mathbf{M}(z, z') \cdot \sum_{\alpha, \beta} \psi_{\alpha}^{\dagger}(z') \hat{\sigma}_{\alpha\beta} \psi_{\beta}(z), \quad (1)$$

and $\psi_{\sigma}^{\dagger}(z)$ and $\psi_{\sigma}(z)$ are the fermionic creation and annihilation operators for a particle with spin σ at site z , respectively, $\hat{\sigma}$ are the Pauli matrices, and $\Delta(z, z') = -\Delta(z', z)$ is the superconducting gap. The $\mathbf{d}$ -vector of the triplet superconductors on the left ($j = L, z < 0$) and right ($j = R, z > 0$) of the barrier is given by $\mathbf{d}_j = (\cos \theta_j, \sin \theta_j, 0)$. We take $\theta_L \equiv 0$ such that $\mathbf{d}_L \parallel \hat{\mathbf{x}}$ and $\theta_R = \theta$ with $\mathbf{d}_R$ lying in the spin xy -plane. The ferromagnetic junction, located at $z = 0$, possesses a moment M_0 and represents a magnetic scattering potential, described by the last term in Eq.(1), with $\mathbf{M}(z, z') = M_0(\cos \alpha, \sin \alpha, 0)\delta(z)\delta(z')$.

We show below that two Andreev bound states with energies $E_{a,b}$ are formed in the TSFTS junction. The Josephson current flows through these two states [11] and

is given by [12]

$$I_J = I_J^a + I_J^b = -\frac{e}{\hbar} \sum_{i=a,b} \frac{\partial E_i}{\partial \Phi} \tanh\left(\frac{E_i}{2k_B T}\right). \quad (2)$$

In order to obtain the energies of the Andreev states, we start from Eq.(1) and derive the Bogoliubov-de Gennes (BdG) equations [12, 13] by introducing the unitary Bogoliubov transformation

$$\begin{aligned} \psi_\uparrow(z) &= \sum_n u_n(z) a_n + v_n(z) b_n^\dagger + w_n(z) b_n + x_n(z) a_n^\dagger, \\ \psi_\downarrow(z) &= \sum_n -u_n(z) b_n + v_n(z) a_n^\dagger - w_n(z) a_n + x_n(z) b_n^\dagger, \end{aligned}$$

where the sum runs over all eigenstates of the junction. For the wave functions of the localized Andreev states on the left and right of the barrier, we make the ansatz

$$\Psi_j(z) = \begin{pmatrix} u_j(z) \\ v_j^*(z) \\ w_j(z) \\ x_j^*(z) \end{pmatrix} = e^{c_j \kappa z} \sum_{\gamma=\pm} A_{j,\gamma} \begin{pmatrix} u_{j,\gamma} \\ v_{j,\gamma}^* \\ w_{j,\gamma} \\ x_{j,\gamma}^* \end{pmatrix} e^{\gamma i k_F z}, \quad (3)$$

where $c_j = +1(-1)$, $j = L(R)$, and κ^{-1} is the decay length of the Andreev state. Using for definiteness a p_z -wave symmetry of the superconducting gap, $\Delta(k_z) = \Delta_j \sin k_z$ (with lattice constant set to unity), the BdG equations take the form $\hat{H}\Psi_j(z) = E\Psi_j(z)$ where

$$\hat{H} = \begin{pmatrix} -\frac{\partial_z^2}{2m} - \mu & ie^{-i\theta} \Delta_j \partial_z & e^{-i\alpha} M_0 \delta(z) & 0 \\ ie^{i\theta} \Delta_j^* \partial_z & \frac{\partial_z^2}{2m} + \mu & 0 & e^{i\alpha} M_0 \delta(z) \\ e^{i\alpha} M_0 \delta(z) & 0 & -\frac{\partial_z^2}{2m} - \mu & ie^{i\theta} \Delta_j \partial_z \\ 0 & e^{-i\alpha} M_0 \delta(z) & ie^{-i\theta} \Delta_j^* \partial_z & \frac{\partial_z^2}{2m} + \mu \end{pmatrix}.$$

In the following we take $\Delta_L = \Delta_0$ and $\Delta_R = \Delta_0 e^{i\phi}$ for the superconducting gap on the left and right side of the junction. The above eigenvalue equation for E is subject to the boundary conditions $\Psi_L(0) = \Psi_R(0)$ and

$$\partial_z \Psi_R(0) - \partial_z \Psi_L(0) = -2mM_0 \begin{pmatrix} 0 & \hat{P} \\ \hat{P}^\dagger & 0 \end{pmatrix} \Psi_R(0), \quad (4)$$

where $\hat{P} = \hat{\sigma}_3 \cos \alpha - i\hat{\sigma}_0 \sin \alpha$. The solution of the BdG equations yields two Andreev states with energies

$$\frac{E_{a,b}}{\Delta_0} = k_F \sqrt{D} \sqrt{A + B - 2C \pm 2\sqrt{(A-C)(B-C)}}, \quad (5)$$

where

$$\begin{aligned} A &= \cos^2(\phi/2) [1 - D \sin^2(\theta/2)], \\ B &= \sin^2(\theta/2) [1 - D \cos^2(\phi/2)], \\ C &= (1 - D) [\cos^2(\phi/2) - \cos^2(\theta/2)] \cos^2(\alpha - \theta/2), \end{aligned}$$

and $D = [1 + g^2]^{-1}$ with $g = mM_0/k_F$. The two Andreev states appear in the local density of states near the




FIG. 2: (a) $\pm E_{a,b}$ and (b) I_J as a function of ϕ for $T = 0$, $\theta = 0$, $D = 0.5$ and several values of α .

junction as two particle-like and two hole-like peaks at energies $\pm E_{a,b}$, respectively.

We first consider $\mathbf{d}_L \parallel \mathbf{d}_R$, and present in Fig. 2 the energies of the Andreev states and the resulting Josephson current at $T = 0$ as a function of ϕ for several values of α . Note that for $T = 0$, only the negative energy branches of the bound states are populated, and thus contribute to I_J . The dependence of $E_{a,b}$ on ϕ is *qualitatively* different for $\mathbf{M} \parallel \mathbf{d}_{L,R}$ and $\mathbf{M} \perp \mathbf{d}_{L,R}$. For $\mathbf{M} \perp \mathbf{d}_{L,R}$ ($\alpha = \pi/2$) the Andreev states are degenerate with $E_{a,b}/\Delta_0 = k_F \sqrt{D} \cos \phi/2$, and possess well defined spin quantum numbers $\sigma_a = \uparrow$, $\sigma_b = \downarrow$, since they are not coupled by the scattering at the ferromagnetic barrier. The zero energy level crossing at $\phi_{LC} = (2n+1)\pi$ (n =integer) occurs with $\partial E_{a,b}/\partial \phi \neq 0$, resulting in discontinuous jumps of I_J , as shown in Fig. 2(b). It is interesting to note that $E_{a,b}$ is identical to that of Andreev states near a potential scattering barrier [6]. In contrast, for $\alpha \neq \pi/2$ the ferromagnetic barrier couples the Andreev states, yielding a splitting of their energies, as shown in Fig. 2(a) for $\mathbf{M} \parallel \mathbf{d}_{L,R}$ ($\alpha = 0$). This coupling yields $\partial E_{a,b}/\partial \phi = 0$ at ϕ_{LC} , such that I_J evolves continuously with ϕ [Fig. 2(b)]. While these results remain qualitatively unchanged with decreasing D , the dependence of I_J on D changes with the orientation of $\mathbf{M}$ and $\mathbf{d}_{L,R}$. Specifically, for $D \ll 1$ one finds, to leading order in D , $I_J \sim D^{1/2}$ for $\alpha \neq 0$, but $I_J \sim D^{3/2}$ for $\alpha = 0$. Finally, note that for $\phi = 0$ and any α , the induced Andreev states with $E_{a,b}/\Delta_0 = k_F \sqrt{D}$ are identical to the impurity (Shiba) states [14] induced by a single (static) magnetic impurity in a 1D triplet superconductor.

The Josephson current in a TSFTS junction exhibits an unconventional temperature dependence in that I_J can change sign, and thus its direction, with increasing temperature, as shown in Fig. 3(a) for $\theta = 0$ and $\phi = \pi/2$ (we assumed a BCS temperature dependence of the superconducting gap). In order to understand this sign change, we consider the ϕ -dependence of $E_{a,b}$ shown in Fig. 3(b) and note that at $T = 0$, only the branches indicated by 1 and 2, belonging to Andreev states a and b , respectively, are occupied. Since the derivatives $\partial E_{a,b}/\partial \phi$ possess opposite signs for the two Andreev states, the corresponding currents through them, $I_J^a < 0$ and $I_J^b > 0$,




FIG. 3: (a) I_J as a function of T/T_c for $\theta = 0$, $\phi = 0.5\pi$ and $D = 0.2$. (b) $\pm E_{a,b}$ as a function of ϕ for $\alpha = 0$. The dotted line corresponds to the parameters in (a).

flow in opposite directions with $I_J^b > |I_J^a|$. With increasing temperature, the occupation of branches 2 and 3 changes more rapidly than those of branches 1 and 4. As a result, the magnitude of I_J^b decreases more quickly than that of I_J^a , and the total current, I_J , eventually changes sign. Moreover, the qualitative nature of the temperature dependence can be altered via a rotation of $\mathbf{M}$. Specifically, as α increases, the $T = 0$ value of I_J^a decreases while I_J^b remains practically unchanged. This leads to a qualitative change in the temperature dependence of I_J such that for $\alpha \geq 0.21\pi$, I_J does not undergo a sign change with increasing temperature [Fig. 3(a)].

The unique dependence of I_J on ϕ and on the orientation of $\mathbf{M}$ can be used to build a Josephson current switch in which I_J is turned “on” or “off” via the rotation of $\mathbf{M}$. This is shown in Fig. 4(a) where we present I_J as a function of α for $\mathbf{d}_L \parallel \mathbf{d}_R$ at $T = 0$. Note that the




FIG. 4: (a) I_J and (b) $\pm E_{a,b}$, as a function of α for $D = 0.5$ at $T = 0$, $\theta = 0$ and several values of ϕ .

α -dependence of I_J changes significantly with increasing ϕ . In particular, I_J becomes sharply peaked around $\alpha = (2n + 1)\pi/2$ with integer n (i.e., for $\mathbf{M} \perp \mathbf{d}_{L,R}$) as ϕ approaches π . As a result, small variations in α lead to large changes in the magnitude of the Josephson current, and can thus tune the junction between an “on”-state ($I_J \neq 0$) and an “off”-state ($I_J \approx 0$). This behavior of I_J is directly reflected in the α -dependence of the bound state energies, as shown in Fig. 4(b). While for $\phi = 0$ the Andreev states are α -independent (see above), $E_{a,b}$ oscillate sinusoidally with α for $\phi = \pi/4$, as shown in Fig. 4(b). As ϕ approaches π (see, e.g., $\phi = 0.9\pi$), the energies of the Andreev states alternate

in being close to zero and almost α -independent for half of the period and sinusoidal for the other half. Finally, for $\phi = \pi$ (not shown) the bound state energies are given by $E_a/\Delta_0 = 2k_F\sqrt{D(1-D)}\cos\alpha$ and $E_b = 0$. Note that for $\phi \leq \pi$, the Andreev states exhibit no zero-energy crossings when $\mathbf{M}$ is rotated.

Another type of Josephson switch can be created by rotating $\mathbf{d}_R$ for fixed $\mathbf{M}$ and $\mathbf{d}_L$, as shown in Fig. 5 for $T = 0$. For $\alpha = 0$, $\phi = \pi/2$ and $D = 0.7$, I_J exhibits




FIG. 5: I_J as a function of θ for $T = 0$, $D = 0.7$, several values of ϕ , and (a) $\alpha = 0$, (b) $\alpha = \pi/4$, and (c) $\alpha = \pi/2$. (d) I_J for $D = 0.2$ and $\alpha = 0$.

an almost perfect square wave form, is symmetric around $\theta = n\pi$, and is nearly θ -independent between the discontinuous jumps, as shown in Fig. 5(a). For $\phi \neq \pi/2$, this symmetry is broken, and the ranges of θ over which I_J is positive or negative are unequal, but the discontinuous jumps in I_J persist. For $\alpha = \pi/4$, the Josephson current is skewed, and in some regions varies nearly linearly with θ [Fig. 5(b)]. For $\alpha = \pi/2$ and $\phi = \pi/2$, I_J is again symmetric around $\theta = n\pi$ [Fig. 5(c)]. With decreasing D , the Josephson current becomes θ -dependent between discontinuous jumps, even for $\alpha = 0$ and $\phi = \pi/2$ [Fig. 5(d)]. Thus small changes in the relative alignment of the $\mathbf{d}$ -vectors can switch the junction between two *current states* with opposite direction of I_J .

A third type of Josephson switch can be formed via a correlated rotation of $\mathbf{M}$ and $\mathbf{d}_R$. Specifically, we note that $E_{a,b}$, Eq.(5), depends on α only via $\cos^2(\alpha - \theta/2)$. We therefore consider a simultaneous rotation of $\mathbf{d}_R$ and $\mathbf{M}$ such that $\alpha = \theta/2$, and present the resulting I_J as a function of θ in Fig. 6(a). I_J then exhibits square wave oscillations with discontinuous jumps from $I_J \approx 0$ to a negative (positive) value for $0 \leq \phi \leq \pi$ ($\pi \leq \phi \leq 2\pi$). To understand these sharp transitions, we plot the ϕ -dependence of $-E_{a,b}$ in Fig. 6(b) (only these branches contribute to I_J at $T = 0$). For $\theta = \pi$ the Andreev states are degenerate, with $\partial E_{a,b}/\partial\phi \leq 0$ (≥ 0) for $0 \leq \phi \leq \pi$ ($\pi \leq \phi \leq 2\pi$). In contrast, for $\theta = \pi/2$ the degeneracy of the Andreev states is lifted with $\partial E_a/\partial\phi \approx -\partial E_b/\partial\phi$ in some range of ϕ (shown as dashed lines in Fig. 6(b)) such that $I_J \approx 0$, but $I_J \neq 0$ in other regions of ϕ (shown as solid lines). Note that as ϕ increases from zero, the




FIG. 6: Correlated rotation of $\mathbf{M}$ and $\mathbf{d}_R$ with $\alpha = \theta/2$ and $D = 0.01$ at $T = 0$. (a) I_J as a function of θ , and (b) $-E_{a,b}$ as a function of ϕ .

range in θ in which $I_J \neq 0$ increases, while the magnitude of I_J decreases. This correlated rotation thus represents another type of Josephson current switch in which I_J can be turned “on” or “off”.

Above, we computed I_J assuming that the phase difference between the superconductors, ϕ , or the relative orientations between $\mathbf{M}$ and $\mathbf{d}_{L,R}$ (i.e., α and θ) are maintained for a sufficiently long time such that the system is in thermodynamic equilibrium. The qualitative form of I_J changes, however, if $\mathbf{M}$ or $\mathbf{d}_{L,R}$ are rotated adiabatically on a time scale which is shorter than the relaxation time required for the occupation of the Andreev states to achieve their equilibrium values. In this case, the occupation of the Andreev states remains unchanged from an initial value during the adiabatic rotation [15]. The




FIG. 7: (a) I_J at $T = 0$ for an adiabatic rotation of $\mathbf{M}$ and in equilibrium (see also Fig. 5(a)) as a function of θ . $\alpha = 0$, $\phi = \pi/2$ and $D = 0.7$. (b) $\pm E_{a,b}$ as a function of θ . The black solid lines represent the occupied states if θ is changed adiabatically.

Josephson current at $T = 0$ for an adiabatic rotation of $\mathbf{d}_R$ and in the equilibrium case are shown in Fig. 7(a). To understand the *qualitative* form of I_J , we note that in the equilibrium case, only the negative energy branches of the Andreev states contribute to I_J . In contrast, if θ is adiabatically changed (from the state with $\theta = 0$ that is in thermodynamic equilibrium), then the energy branches of the Andreev states represented by the black solid lines in Fig. 7(b) remain occupied, while those shown as red dashed lines remain unoccupied. As a result, I_J in the adiabatic case changes continuously with θ and does not exhibit the discontinuous jumps shown by the equilibrium I_J . Note that I_J is 2π -periodic in both cases. A

special case arises for $\alpha = \pi/2$, when the periodicity of I_J is changed to 4π (not shown). An adiabatic change of ϕ also leads to a 4π -periodicity of I_J , in analogy to the fractional *ac*-Josephson effect discussed in Ref. [6].

Finally, scattering off the ferromagnetic barrier in general leads to a suppression of the superconducting order parameter near the barrier, which was not accounted for in the above approach. However, in nodeless superconductors, such as the one discussed above, the order parameter recovers its bulk value on a length scale set by $1/k_F$ [16], which is assumed to be much shorter than the decay length of the Andreev bound state [6, 12]. As a result, the spatial variation of the order parameter leads to only weak quantitative and no qualitative changes in the induced fermionic bound states [16]. We thus expect that the results presented above are unaffected by the inclusion of the order parameter suppression.

In summary, we predict a new type of Josephson effect in TSFTS junctions, in which I_J exhibits a rich dependence on the relative orientation of $\mathbf{M}$ and $\mathbf{d}_{L,R}$. This dependence can be used to build several types of *Josephson current switches* in which small changes of α or θ can tune the junction between two *current states*. We predict an unconventional temperature dependence of I_J such that for certain orientations of $\mathbf{M}$ and $\mathbf{d}_{L,R}$, I_J changes sign with increasing temperature.

We are grateful to F. Nogueira and A. Sudbø for helpful discussions. D.K.M. acknowledges financial support from the Alexander von Humboldt foundation.

-
- [1] For recent reviews see S. Kashiwaya and Y. Tanaka, Rep. Prog. Phys. **63**, 1641 (2000); A.A. Golubov *et al.*, Rev. Mod. Phys. **76**, 411 (2004); and references therein.
 - [2] Yu. S. Barash *et al.*, Phys. Rev. Lett. **77**, 4070 (1996); Y. Tanaka and S. Kashiwaya, Phys. Rev. B **53**, R11 957 (1996); S.K. Yip, J. Low Temp. Phys. **109**, 547 (1997).
 - [3] R.A. Riedel and P.F. Bagwell, Phys. Rev. B **57**, 6084 (1998).
 - [4] Y. Asano *et al.*, Phys. Rev. B **67**, 184505 (2003); Y. Asano *et al.*, J. Phys. Soc. Jpn. **73**, 1922 (2004).
 - [5] C.D. Vaccarella *et al.*, Physica C **391**, 89 (2003).
 - [6] H.-J. Kwon, K. Sengupta, and V.M. Yakovenko, Eur. Phys. J. B **37**, 349 (2004).
 - [7] C.R. Hu, Phys. Rev. Lett. **72**, 1526 (1994); L.J. Buchholtz and G. Zwicknagl, Phys. Rev. B **23**, 5788 (1981); M. Fogelström, *et al.*, Phys. Rev. Lett. **79**, 281 (1997).
 - [8] Changing the orientation of $\mathbf{M}$, can, for example, be achieved by applying a local magnetic field to the barrier via atomic force microscopy [9].
 - [9] P.C. Hammel, Nature (London) **430**, 300 (2004).
 - [10] B.E. Kane, Nature (London) **393**, 133 (1998).
 - [11] The Josephson current carried by states outside the superconducting gap is in general negligible [3, 12].
 - [12] A.M. Zagoskin, *Quantum Theory of Many-Body Systems* (Springer, New York 1998).
 - [13] P.G. de Gennes, *Superconductivity of Metals and Alloys* (Addison-Wesley, New York, 1989).

- [14] Y. Lu, Acta Physics Sinica **21**, 75 (1965); H. Shiba, Prog. Theoret. Phys. **40**, 435 (1968).
- [15] J. J. A. Baselmans *et al.*, Nature (London) **397**, 43 (1999).
- [16] P. Schlottmann, Phys. Rev. B **13**, 1 (1976); M.I. Salkola *et al.*, Phys. Rev. B **55**, 12648 (1997).